

ASHLAND CHEMICAL COMPANY -- PLIOBOND-30 -- 8040-00-543-7170

===== Product Identification =====

Product ID:PLIOBOND-30

MSDS Date:10/30/1991

FSC:8040

NIIN:00-543-7170

MSDS Number: BVTXQ

=== Responsible Party ===

Company Name:ASHLAND CHEMICAL COMPANY

Box:2219

City:COLUMBUS

State:OH

ZIP:43216-2219

Country:US

Info Phone Num:614-790-3333

Emergency Phone Num:614-790-3333/800-424-9300(CHEMTREC)

CAGE:3489

7

=== Contractor Identification ===

Company Name:ASHLAND CHEMICAL CO

Box:2219

City:COLUMBUS

State:OH

ZIP:43216-2219

Country:US

Phone:614-790-3333/800-274-5263

CAGE:34897

Company Name:RUSCOE W J CO

Address:485 KENMORE BLVD

Box:3858

City:AKRON

State:OH

ZIP:44314

Country:US

Phone:216-253-8148

CAGE:86839

===== Composition/Information on Ingredients =====

Ingred Name:SYNTHETIC RUBBER

Fraction by Wt: 13 - 17%

Other REC Limits:NONE RECOMMENDED

Ingred Name:ALKYL PHENOLIC RESIN

Fract

ion by Wt: 8 - 12%

Other REC Limits:NONE RECOMMENDED

Ingred Name:CALCIUM CARBONATE

CAS:471-34-1

RTECS #:FF9335000

Fraction by Wt: 1 - 5%

Other REC Limits:NONE RECOMMENDED

OSHA PEL:15 MG/M3 TDUST

ACGIH TLV:10 MG/M3 TDUST

Ingred Name:METHYL ETHYL KETONE (2-BUTANONE) (MEK) (SARA III)

CAS:78-93-3

RTECS #:EL6475000

Fraction by Wt: 70%

Other REC Limits:NONE RECOMMENDED

OSHA PEL:200 PPM

ACGIH TLV:200 PPM/300STEL 9394

EPA Rpt Qty:5000 LBS

DOT Rpt Qty:5000 LBS

Ingred Name:PHENOL (SARA III) (SARA III

)

CAS:108-95-2

RTECS #:SJ3327000

Fraction by Wt: 1

Spec Gravity:0.893

Evaporation Rate & Reference: