

View Online at <https://aerobasegroup.com/nsn/1005-00-056-5775>

General Description:

Material steel, cre mil-s-22216. Comp 1c-322a except omit paragraph 3.5.2, 4.2.2.1, 4.2.2.2, and 4.2.2.3 (type 17-4ph). Heat treat to condition h1125 per mil-h-6875 to following mechanical properties: 135,000 psi ultimate tensile, 110,000 psi yield, and 15 percent elongation

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli