

View Online at <https://aerobasegroup.com/nsn/1005-00-501-3541>

General Description:

Steel, qq-s-700 or astm a108, 1045 or 1050; 2.176 in. Lg.; 1.448 in. W.; 0.1875 in. High; heat treatment= carburize for 5-7 min. At 1575-1600 deg. F., oil quench, temper 1 hr. Min. To rockwell hardness 15n 89-91.5; manganese phosphate, type m, class 1, or zinc phosphate, type z, class 1, per mil-p-16232; 1 hole 0.1875 in. Dia.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli