

View Online at <https://aerobasegroup.com/nsn/1005-00-514-0137>

End Application:

MACH-IN-EGU-N,CA

General Description:

Steel, cmpsn 1018-1022 or 1118, astm-a108; 1.497 in. Dia.; 0.395 in. Dia.; central hole is 0.627 in. Dia.; heattreatment=carburize at 1575-1625 deg. F. To case depth of 0.007-0.010 in., oil quench, temper 30 min. At 350 deg. F.Min. To rockwell hardness 15n88-92; 50notches equally spaced along edge

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli