

View Online at <https://aerobasegroup.com/nsn/1005-00-556-4278>

End Application:

MACH-IN-EGU-N,,5

Special Features:

Stress relieve at 1050 degrees f for 1 hr; heat at 1500/1550 degrees f; quench in salt at 700 degrees f; hold 45 min, air cool; reheat; oil quench; temper 1 hr; finish: 125 micro inches; harden to rockwell c51-c59; ctr hole 0.375 in. Diameter located 4.340 in. From 1st end; matl-steel or steel astm a331; surface treat. -phosphate manganese or phosphate zinc

Material:

Steel

Surface Treatment:

Phosphate

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A23900