

View Online at <https://aerobasegroup.com/nsn/1005-00-586-0774>

End Application:

PIST-OL-,AU-TO;C

General Description:

Vsteel, alloy s.A.E. 1075-1085, astm a576 or astm a675 or qq-s-700, austentic grain size 7 or finer; 0.617 in. Lg; 0.368 in. W; 0.136 in. Thk; 1 hole 0.1565 in. Dia; 1 hole 0.2045 in. Dia; 0.291 in. Center of hole 1 to center of hole 2; heat treatment-austenitize at 1540-1580 degrees f in neutral salt or atmosphere, quence in austempering salt at approx 640 degrees f, hold for 30 min; surface treatment-manganese phosphate, dod-p-16232, type m, class 2; link is marked with, 13, in designated location

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli