

View Online at <https://aerobasegroup.com/nsn/1005-00-587-8385>

**General Description:**

C/omatl: steel, spec astm a304, a322, a331, 4140, 8640, 8645, 8740; heat treatment: heatat 1525-1550 degrees f ; quench in circulating oil. Temper 30min at heat to hardness specified; rockwell hardness c32-40; final protective finish: finish 5.3.1.2 of mil-std-171; wd 0.504 in; 2 through holes with inside diameter of 0.594 and 0.801 in

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli