

View Online at <https://aerobasegroup.com/nsn/1005-00-587-8386>

General Description:

Material: steel astm a506, 8640, 8645; final protective finish 5.3.1.2 of mil-std-171; heat treat to 1525- 1550 degrees f quench in circulating oil, temper 45 min at heat to rockwell hardness c40-45; lg 6.500 in; wd 0.567in

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli