

View Online at <https://aerobasegroup.com/nsn/1005-00-600-8872>

General Description:

C/omatl: steel, astm a684: 1055 or 1065; heat treat; heat to 1500-1550 decoil quench; temper 20 min to rockwell hardness a73-76; final finish: finish 5.3.1.2 or 5.3.2.2 of mil-std-171; lg 1.865 in

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli