

View Online at <https://aerobasegroup.com/nsn/1005-00-690-0316>

General Description:

Steel, grade 8640, astm a322 or a331; heat at 1540-1580 deg. F., oil quench, temper 30 min. At 450 deg. F. Min. To hardness specified; manganese phosphate, type m, or zinc phosphate, type z, per mil-p-16232, class 1; 4.642 in. Lg.; 0.372 in. W.; 0.304 in. Thk.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli