

View Online at <https://aerobasegroup.com/nsn/1005-00-690-0605>

**General Description:**

Steel, qq-s-624, 6650, 4150, 4140; heat treatment=heat at 1525-1550 deg. F., oil quench, temper 30 min. At heat to hardness specified; manganese phosphate, type m, or zinc phosphate, type z, per mil-p-16232, class 1; 1.985 in. Lg.

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli