

View Online at <https://aerobasegroup.com/nsn/1005-00-690-0611>

General Description:

Steel, grade 8620, astm a322 or a331; heat treatment=carburize at 1575-1625 deg. F. To case depth 0.005-0.008 in., oil quench, temper 30 min. At 350 deg. F.; manganese phosphate, type m, or zinc phosphate, type z, per mil-p-16232, class 1; 3.495 in. Lg.; 1.000 in. W.; 0.305 in. Thk.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli