

View Online at <https://aerobasegroup.com/nsn/1005-00-690-0619>

General Description:

Steel, grade 4140, 8640, or 8740, per ASTM A322 or A331; heat at 1525-1550 deg. F., oil quench, temper 1 hr. At heat to hardness specified; manganese phosphate, type M, or zinc phosphate, type Z, per MIL-P-16232, class 1; 7.332 in. Lg.; 0.830 in. W.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli