

View Online at <https://aerobasegroup.com/nsn/1005-00-711-0505>

General Description:

Steel, astm a322, 8620; heat treatment=carburize at 1575-1600 deg.F. To acase depth of 0.008 to 0.012 in., oil quench, temper 1 hr. Min. At 350-450 deg. F. To hardness specified; manganese phosphate, type m, class 1, or zinc phosphate, type z, class 1, per mil-p-16232; 5.000 in. Lg.; 0.733 in. W.; 0.248 in. Thk.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli