

View Online at <https://aerobasegroup.com/nsn/1005-00-711-1777>

End Application:

Mg cal.50 m85 fixed

General Description:

Steel, astm a684, 1055 or 1065, type1; heat treat to 1485-1525 deg. F., oilquench, temper 30 min. At heat to hardness specified; manganese phosphate, type m, class 1, or zinc phosphate, type z, class 1, per mil-p-16232; 2.797 in. W.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fig:

A23900