

View Online at <https://aerobasegroup.com/nsn/1005-00-711-4526>

End Application:

Machine gun, .50cal , m85

General Description:

Asteel, astm a322: 8620; 0.344 in.Diaat widest point; 0.822 in.Lg; surface treatment: manganese phosphate, mil-p-16232, type m, class 1;

heat treatment: carburize at 1575 to 1625 degrees f.T per 30 minutes

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli