

View Online at <https://aerobasegroup.com/nsn/1005-00-716-1302>

End Application:

MACH-IN-EGU-N,CA

General Description:

Steel, astm a322 or a331, 4140, 4150, or 8650; 1.467 in. Lg.; 1.375 in. W.; 0.6215 in. Thk.; heat at 1500-1575 deg. F., oil quench, temper 1 hr. Min. To rockwell c53-59, no decarburization allowed; 1 hole 0.282 in. Dia., csk 90 deg.Both sides; manganese phosphate, type m, or zinc phosphate, type z, per mil-p-16232, class 1

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fiig:

A23900