

View Online at <https://aerobasegroup.com/nsn/1005-00-840-1979>

**General Description:**

Steel, cmpsn 1018 through 1022, astm a108; carburize at 1575 degrees f to 1600 degrees f to case depth; oil quench; temper 30minutes at 325 degrees f min to hardness specified; 0.350 in l; 0.186 in outside dia; 0.109 inside dia

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli