

View Online at <https://aerobasegroup.com/nsn/1005-00-922-8059>

General Description:

Jsteel, qq-s-637, 1141, 1137, or astm a108, 1032-1045; heat at 1525-1575 deg. F., quench in agitated oil, temper 45 min. At heat to hardness specified; 2.470 in. Lg.; 1.174 in. W.; 0.497 in. High; 1 hole 0.500 in. Dia.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli