

View Online at <https://aerobasegroup.com/nsn/1005-00-933-8070>

General Description:

Msteel, 4140, 4150, qq-s-624; heat at 1535-1565 deg. F., oil quench, temper immediately for 1 hr. At heat to hardness specified; manganese phosphate, type m, or zinc phosphate, type z, class 1; 6.000 in. Lg.; 1.750 in. Dia.

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli