

View Online at <https://aerobasegroup.com/nsn/1005-00-981-1252>

General Description:

Steel, alloy 4140, 4145, 8645, or 8740, astm a322 or astm a331; 0.380 in. Lg.; 0.370 in. Dia.; heat at 1540-1600 deg. F., quench in circulating oil, temper 30 min. At heat to hardness rockwellc42-45; manganese phosphate, type m, or zinc phosphate, type z, per mil-p-16232, class 1

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli