

View Online at <https://aerobasegroup.com/nsn/1005-01-130-0772>

**General Description:**

Viton compound no. 4059 material may be purchased from jasper rubber products, inc., 1010 first ave, jasper, indiana 47546 fscm: none; tensile strength 1300 psi min, elongation 65 degrees f 300 percent min, minus 50 degrees f 50 percent min, swell 72 hours exposure to aero shell no. 17 grease mil-g21164c at 70 degrees c 5 percent maximum volume change, length 14.360 in. Porm 0.010 in.

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli