NSN 1005-01-204-4341

Firing Pin Guide - Page 1 of 1



View Online at https://aerobasegroup.com/nsn/1005-01-204-4341

General Description:

Omaterial: steel; 16.025 in.Lg; 9.500in.W; 8.200 in.Th; hardened to rockwell c 40-45; heat at 400 degrees c; harden at 850 degrees c; quench

at 180 degreesc for 10 minutes in salt; wash, pickle, neutralize; surface finish: black oxide, mil-c-13924, class 1

Shelf Life:

N/a

Unit Of Measure:

Demilitarization:

Yes - demil/mli

Fiig:

A23900