

View Online at <https://aerobasegroup.com/nsn/1005-01-204-4352>

**General Description:**

Material: steel; 38.75 mm lg; 10.95 mm w; heat at 400 degrees c; harden at 850 degrees c; quench at 180 degrees c for 10 minutes in salt; wash, pickle, neutralize; surface treatment: manganesephosphate, mil-p-16232, type m, class 1; surface hardened to rockwell c 40-45

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fiig:**

A23900