

View Online at <https://aerobasegroup.com/nsn/1005-01-393-2755>

End Application:

Mh-53j aircraft

General Description:

Steel alloy 4130, condition c or d, per mil-s-6758; heat treat 150,000 psi min t.S. Rockwell c34-38 per mil-h-6875; 2.510 in. Lg o/a; 0.625 in. W o/a; 2 bolt holes, 0.3125-24unf-3b; 1.500 in. Bolt circle dia

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fig:

A23900