

View Online at <https://aerobasegroup.com/nsn/1010-00-438-7439>

**General Description:**

Wrought material: steel, comp 4340mil-s-5000; investment casting: steel comp 1c4340, mil-s-22141; heat treatment; wrought material: 1450deg f to 1550 degrees f oil quench; investment casting: 1550 degrees f to 1600 degrees foil quench; finish: 125 microinches; final protective finish 5.3.1.2 of mil-std-171; 1.280 l, 1.160 w, 0.980 hhardness rockwell c38-42

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli