

View Online at <https://aerobasegroup.com/nsn/1015-01-188-7864>

General Description:

Xsteel alloy, 4340, cond. Annealed, per mil-s-5000 or ams 6415; 2.500 in. Lg.; 1.880 in. W.; 0.810 in. Thk.; heattreatment: harden and temper to rc 40-43 per mil-h-6875; surface treatment is phosphate coating, mil-p-16232, type m, class 2

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli