

View Online at <https://aerobasegroup.com/nsn/1025-00-071-0753>

General Description:

Material: steel casting, class 105-85, spec qq-s-681..32 carbon maximum or tube, alloy steel, cmpsn 4130 or 8630, condition-normalized, astm a519; quench and temper to rockwell c20-25; steel weld per class 3, mil-std-1261; pressure test must maintain 5000 psi oil pressure for 5 minutes; o/a 23.438 in long; outside diameter 5.000 in; inside diameter 3.495 in

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli