

View Online at <https://aerobasegroup.com/nsn/1240-01-073-7289>

General Description:

Material: al aly sand casting; stress releive at 300 degrees f to 350 degrees f for 1.5 hours, air cool at room temperature

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli