

View Online at <https://aerobasegroup.com/nsn/1315-01-163-5426>

General Description:

Staballoy matl; 16.805 in. O/a long; a total of 56 buttress profiles reqd from starting surface extending 9.00 in. Length by 1.076 in. Outside dia; one end threaded, 0.8125-16un-2a-lh with 0.800 thread fastening length; second end, 0.420 in. Spherical radius; chemical properties as cast matl - depleted uranium, titanium content (by wt) 0.69 pct, carbon 0.008 pct, iron, nickel and copper 0.005 pct each, silicon 0.015 pct; c40-c45 rockwell hardness; 185, 000 psi min tensile strength; 105, 000 psi min (0.2 pct offset) yield strength; used on crtg 105mm apfsds-t, xm833

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli