

View Online at <https://aerobasegroup.com/nsn/1376-01-132-1691>

General Description:

This specification covers ethyl cellulose for injection molding, and extrusion for rocket grain inhibiting materials; type ii, class 1, tensile strength, mpa (psi) min 26 (3800); matl shall consist of plasticized ethyl cellulose thermoplastic compounds - ethyl cellulose flake 100 parts and plasticizer 31 to 35 parts; color is light amber; the molding matl is used in producing film and molded parts for use with rocket propellant grain (ballistic type)

Specification Or Standard:

ii type and 1 class

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli