

View Online at <https://aerobasegroup.com/nsn/1420-01-045-3173>

End Application:

Missile model aim-9l

General Description:

Bake in vacuum oven 0.4 psia maximum at 405 degrees for 4 hrs, specular reflectance 96 percent from 2 through 6 micrometers wavelength, reflectance angle of incidence from 10 through 15 degrees, surface m shall be 80-20 scratch and dig in a/w mil-0-13830

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli