

View Online at <https://aerobasegroup.com/nsn/1560-01-338-9584>

**End Application:**

1560-01-054-9512 windshield panel s-3a/b acft

**Aircraft Location:**

Windshield

**Aircraft Mission Design Series:**

S-3a/b

**Special Features:**

60313 clear chemcor chemically strengthened, modulus of rupture 16000 psi min., central tension 6500 psi max. 4000 psi min., case depth 0.017 min., anti-static coating, surface resistivi type 1k-25 meg ohms per sq., face ply 0.105 in. X 41.0 in. X 41.0 in.

**Material:**

Glass

**Surface Treatment:**

Oxide

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fig:**

A11700