

View Online at <https://aerobasegroup.com/nsn/1560-01-502-6763>

End Application:

C-17 aircraft

General Description:

Fdms 2288 t3c2ge; ply thickness 0.0045"; areal weight 104 g/m2; fiberglass cloth prepreg (stage b); weave is style 120; resin content 39% by weight; store and ship at 10f or below; shelf life when new: 180 days, rebewable to 90 days then 30 days; shelf life is guarenteed to be at least 50 days upon receipt; total allowable out of freezer time is 14 days; cure at 250f; serviceable temperature range -65f to +160f; u/i is 38"wide; mininum order is 25 yds

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli