

View Online at <https://aerobasegroup.com/nsn/1560-01-502-6766>

End Application:

C-17 aircraft

General Description:

Dms 2288 t3c4gf; ply thickness 0.01"; areal weight 293 g/m2; fiberglass cloth prepreg (stage b); weave is plain style 181; resin content 45% by weight; store and ship at 10f or below; shelf life when new: 180 days, renewable to 90 days then 30 days; shelf life is guaranteed to be at least 50 days upon receipt; total allowable out of freezer time is 14 days; cure at 250f; serviceable temperature range -65f to +160f; u/i is 38"wide; order is 25 yds

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli