

View Online at <https://aerobasegroup.com/nsn/1560-01-502-6774>

**End Application:**

C-17 aircraft

**General Description:**

Dms 2288 t2c2gc; ply thickness 0.0105"; areal weight 280 g/m2; carbon cloth, epoxy prepreg (stage b); weave is 5 harness satin; resin content 39% by weight; store and ship at 10f or below; shelf life when new: 180 days, renewable to 90 days then 30 days; shelf life is guaranteed to be at least 50 days upon receipt; total allowable out of freezer time is 14 days; cure at 250f; serviceable temperature range -65f to +160f; order is 5 yds

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli