

View Online at <https://aerobasegroup.com/nsn/1560-01-502-7191>

Special Features:

Prepreg carbon cloth

General Description:

Ldms2288 t2c2gb; p/w 250, ply thickness 0.0075", carbon cloth, epoxy prepreg (stage b); weave is plain weave; areal weight 193 g/m2; resin content 39% by weight; store and ship at 10f or below; shelf life when new: 180 days, renewable to 90 days then 30 days; shelf life is guaranteed to be at least 50 days upon receipt; total allowable out of freezer time is 14 days; cure at 250f; serviceable temperature range -65f to +160f; u/i is 60" wide; order is 4 yds

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli