

View Online at <https://aerobasegroup.com/nsn/1560-01-502-7192>

Special Features:

Epoxy cloth

General Description:

Dms 2224 t1cwgs, carbon cloth, epoxy prepreg (stage b); weave is 5 harness satin, 3k; resin content 37% by weight; store and ship at 10f or below; shelf life when new: 180 days, renewable to 90 days then 30 days; shelf life is guaranteed to be at least 50 days upon receipt; total allowable out of freezer time is 14 days; cure at 350f; serviceable temperature range -65f to +200f; roll is 60" wide

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli