

View Online at <https://aerobasegroup.com/nsn/1560-01-516-8744>

**Special Features:**

Material is weave style 51789 nylon 6.6 fiber with bismaleimade resin; cure temp 177 degrees c +/- 5 degrees (350 degrees f +/- 5 deg) for 4 hours at 177 degrees c (350 degrees f); item shall be stored at or below -18 degrees c (0 degrees f) for six months after date of shipment, when stored at this temp item doesn't need retesting prior to 720 days from date of shipment

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli

**Fig:**

A556k0