

View Online at <https://aerobasegroup.com/nsn/1650-00-104-5675>

General Description:

Material is corrosion resistant steel, per ams 5355; nickel plated per qq-n-290, class 2 or ams 2404; heat treat-preheat at 1450 degrees fahrenheit; austenized 1800 degrees min and 1850 degrees maximum fahrenheit for 20 minutes min at neutral atmosphere and air cool, double temper at 1100 degrees 5 min air cooling to produce hardness of 36-41 rockwell c; length is 2.104 in. Min and 2.434 in. Max; width is 1.056 in. Min and 1.101 in. Max

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli

Fig:

A042a0