

View Online at <https://aerobasegroup.com/nsn/1650-01-034-3710>

End Application:

P/n 714950a; e3a acft

General Description:

Steel, ams 6260; carburize, harden, and freeze; 80-83 ra hardness; 0.006-0.015 case depth; 2.352 in. O/a lg; 0.562 in. Od, 0.312 in. Id, w/0.500 in. Diameter groove, first end; 0.750 in. Od, 0.406 in. Id, w/0.500 in. Groove dia, second end

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli