

View Online at <https://aerobasegroup.com/nsn/1680-00-008-9406>

General Description:

Nitralloy, mil-s-6709, phosphate coat per mil-c-490 grade 1, rockwell c 34-38 core hardness, nitride all over to rockwell 15n 0.003 in.Min, 0.006 in. Maximum effective case depth 0.0003 maximum white layer, 0.380 in.0.400 in. O/a lg, 0.246 in. Min, 0.248 in. Maximum dia, 0.206 in. Min, 0.210 in.Max by 0.22 in. Min, 0.24 in. Maximum deep large id, 0.199 in. Min, 0.200 in.Max small od

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No