

View Online at <https://aerobasegroup.com/nsn/1680-00-343-8032>

**General Description:**

Cast per qq-a-596 comp 8 356-t6 aluminum alloy, min ult ts 33000 psi, min yield ts 22000 psi, min elongation in 2 in - 3 percent

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli