

View Online at <https://aerobasegroup.com/nsn/1680-01-005-6256>

**End Application:**

Acft, model f-5e

**General Description:**

Steel, mil-s-5626, e4140, condition c-4, phosphate coat, mil-p-16232, type m, class 2, 45 to 48 rockwell hardness, 210, 000 to 250, 000 psi tensile strength, 7.590 in. Lg, 0.580 in. Dia

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli