

View Online at <https://aerobasegroup.com/nsn/1680-01-103-6531>

**End Application:**

F-16 acft

**General Description:**

Nitralloy mod 135, mil-s-6709 cond annealed; heat treat case 62-67 rhc 0.004- 0.006 deep, core 32 rhc min; spline data per a.S.A. B5.15-1960 15 teeth, 48/96 pitch, 30 degrees p.A. Fillet root side fit; pitch diameter 0.313; solid film lubricant 0.0002 in. Thk per mil-I-8937.To all surfaces

**Fsc Application Data:**

Rotary, actuator canopy

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli