

View Online at <https://aerobasegroup.com/nsn/1680-01-114-7218>

End Application:

Kc-135 acft

General Description:

Material is 2014-t6511 aluminum alloy per qq-a-200/2, min tensile strength is 65, 000 psi, min yield is 55, 000 psi, min elongation is 7 percent, tube is 295.80 in. Long, inside diameter is 8.290 in. Min and 8.300 in. Max, outside diameter is 8.480 in. Min and 8.485 in. Max

Fsc Application Data:

Flying boom, acft

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

Yes - demil/mli