

View Online at <https://aerobasegroup.com/nsn/2510-00-168-2405>

**General Description:**

Steel, casting, composition carbon 0.40 pct max, sulphur, 0.06 pct max, phosphorus 0.05 pct max, properties, tensile strength 70, 000 psi min, yield point 40, 000 psi min, elongation in 2 16 pct min, reduction in area 25 pct min, brinell hardness 140-163, annealed, normalized or normalized and drawn

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

Yes - demil/mli