

View Online at <https://aerobasegroup.com/nsn/2520-00-176-8937>

**General Description:**

Plastic, acetal type i class 3 specification l-p-392, anneal inneutral mineral oil at 300 degrees f for 20 min, 0.930 in. H, 0.995in min 0.997 in maximum od, 0.845 in min 0.850 in maximum spherical dia

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No