

View Online at <https://aerobasegroup.com/nsn/2910-00-457-1749>

**General Description:**

Cured polyurethane foam, shelley foam 380, densi type 3.8 lgs/cu ft, tear strength 5 lbs/in., tensile strength 20 psi, elongation 225 percent; 2.140 in. Lg, 1.150 in. W, 0.380 in. Thk

**Shelf Life:**

N/a

**Unit Of Measure:**

--

**Demilitarization:**

No