

View Online at <https://aerobasegroup.com/nsn/3040-01-085-2115>

Special Features:

Steel ams 6260; carburize and harden to enclosed areas to rc-58.0, 0.008 in. Min and 0.013 in. Maximum deep; core and uncarburized areas rc 35.0 min to rc 42.0 max; 5.000 in. Lg; spur gear both ends

Shelf Life:

N/a

Unit Of Measure:

--

Demilitarization:

No

Fiig:

A503n0